



ArmorPoxy Inc.
 1260 North Ave
 Plainfield, NJ 07062
armorpoxy.com
 E: info@armorpoxy.com
 P: 888-755-7361

ARMRNWTX

ARMOR RENEW WOOD AND CONCRETE RESURFACER - TEXTURED

PRODUCT DESCRIPTION

Armor Renew is a high build, water based acrylic coating designed to resurface heavily worn decks and patios.

DECKS: For wood and most composite decks. Follow specific manufacturer's recommendation before applying to any composite decking.

PATIOS: For use on broom swept or porous concrete surfaces. Do not use on smooth or floated concrete. Not recommended for driveways, garages or other areas with vehicular traffic

FOR EXTERIOR USE ONLY

PRODUCT FEATURES

- Ideal for heavily worn decks and patios
- 2 coat system allows for maximum performance
- Excellent weather resistance
- Fills 1/4" cracks
- Available in 30 different colors, *must be tinted before use*
- Low Temperature application down to 40°F
- Super thick coating for extra durability


PRODUCTS TO BE USED WITH

- Renew Textured Roller
- Renew Deck Cleaner
- Renew Wood Deck Primer
- Flash Bond Primer (for Trex type) decking

PHYSICAL PROPERTIES

Resin Type	Water-based Acrylic Polymer
Pigment Type	Varies with color
Solvents	Glycol Ethers, Water
Weight-Per Gallon	12.6 lbs
Weight-Per Liter	1.52 kg
Solids By Weight	68.3%
Solids By Volume	51.3%
Volatile Organic Compounds	<50 g/l (0.42lbs./gal.)
Recommended Dry Film Thickness(DFT)/Coat	20 mils
Practical Coverage (assume 15% material loss)	50-100 sq.ft per gallon Rates will vary based on surface profile
Dry Times (@ 70-80°F (21-27°C) and 50% RH)	---
Touch	4-6 hours
Light Traffic	24 hours
Full Cure	7 days
Shelf Life	3 Years
Flash Point	>200°F (93°C)
Storage	Protect from freezing.
Safety Information	For additional information, see the SDS

BENEFITS



**Fills Cracks
up to 1/4"**



**Available in
over 30 Colors**



**Super Thick
Coating**



**Weather
Resistant**



**Low Temperature
Application**

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.